

COPOLYMER Ethylene – Vinyl Acetate (VA) with high content of VA

Description

EVATANE® 18-150 is a random copolymer of Ethylene and Vinyl Acetate made by high-pressure radical polymerisation process. EVATANE® 18-150 is stabilized with antioxidants.

Main application

The High Vinyl Acetate content of EVATANE® 18-150 brings softness, flexibility and polarity. EVATANE® 18-150 is compatible with tackifying resins and waxes. Combined with a high fluidity, it's a useful product for hot melt adhesives formulation. EVATANE® 18-150 delivers high cohesive strength and compatibility with any kind of fillers (masterbatches, compounds etc.).

Specified properties

Characteristics	Value	Unit	Test Method
Vinyl Acetate Content	17 - 19	% wt	FTIR (Internal)
Melt Index (190°C / 2.16 kg)	135 - 175	g/10mn	ASTM D 1238

Physical properties

Characteristics	Value	Unit	Test Method
Density (23°C)	0.93	g/cm ³	ISO 1183
Melting point	81	°C	DSC
Vicat softening point (1 kg)	41	°C	ASTM D 1525 / ISO 306
Ring & Ball temperature	95	°C	ASTM E28
Elongation at break	600-900	%	ASTM D 638 / ISO R 527
Tensile strength at break	7	MPa	ASTM D 638 / ISO R 527
Hardness Shore A	84	-	ASTM D 2240 / ISO 868

Processing

EVATANE® 18-150 can be processed on any kind of conventional equipment used for thermoplastics. EVATANE® 18-150 should not be overheated during processing and It is recommended to do not have melt temperatures above 230°C and to purge the equipment after a run is completed.

Storage

EVATANE® 18-150 is available in pellet form and commonly packed in 25 kg PE bags on palettes of 1.375 tons. Other packaging can be considered (ask your Arkema's representative).

Precautions of use

A safety data sheet as well as information on handling and storage of the EVATANE® 18-150 are available close to your correspondent ARKEMA or on the site www.arkema.com under heading FDS.

October 2007

The information contained in this document is based on trials carried out by our Research Centers and data selected from the literature, but shall in no event be held to constitute or imply any warranty, undertaking, express or implied commitment from our part. Our formal specifications define the limit of our commitment. No liability whatsoever can be accepted by Arkema with regard to the handling, processing or use of the products concerned which must in all cases be employed in accordance with all relevant laws and/or regulations in force in the country or countries concerned.

