

COPOLYMER Ethylene – Vinyl Acetate (VA) with high content of VA

Description

EVATANE[®] 33-15 is a random copolymer of Ethylene and Vinyl Acetate made by high-pressure radical polymerisation process. EVATANE[®] 33-15 is stabilized with antioxidants.

Main application

The High Vinyl Acetate content of EVATANE[®] 33-15 brings softness, flexibility and polarity. EVATANE[®] 33-15 delivers high cohesive strength with any kind of fillers (HFFR compounds).

Specified properties

Characteristics	Value	Unit	Test Method
Vinyl Acetate Content	30 - 33	% wt	FTIR (Internal)
Melt Index (190°C / 2.16 kg)	14 - 20	g/10mn	ASTM D 1238

Physical properties

Characteristics	Value	Unit	Test Method
Density (23°C)	0.96	g/cm ³	ISO 1183
Melting point	64	°C	DSC
Vicat softening point (1 kg)	<40	°C	ASTM D 1525 / ISO 306
Ring & Ball temperature	128	°C	ASTM E28
Elongation at break	800-1000	%	ASTM D 638 / ISO R 527
Tensile strength at break	15	MPa	ASTM D 638 / ISO R 527
Hardness Shore A	69	-	ASTM D 2240 / ISO 868

Processing

EVATANE[®] 33-15 can be processed on any kind of conventional equipment used for thermoplastics. EVATANE[®] 33-15 should not be overheated during processing and it is recommended to do not have melt temperatures above 230°C and to purge the equipment after a run is completed.

Storage

EVATANE[®] 33-15 is available in pellet form and commonly packed in 25 kg PE bags on palettes of 1.375 tons. Other packaging can be considered (ask your Arkema's representative).

Precautions of use

A safety data sheet as well as information on handling and storage of the EVATANE[®] 33-15 are available close to your correspondent ARKEMA or on the site www.arkema.com under heading FDS/MSDS.

October 2007

The information contained in this document is based on trials carried out by our Research Centers and data selected from the literature, but shall in no event be held to constitute or imply any warranty, undertaking, express or implied commitment from our part. Our formal specifications define the limit of our commitment. No liability whatsoever can be accepted by Arkema with regard to the handling, processing or use of the products concerned which must in all cases be employed in accordance with all relevant laws and/or regulations in force in the country or countries concerned.

