

COPOLYMER Ethylene – Vinyl Acetate (VA) with high content of VA

Description

EVATANE[®] 33-45 PV is a random copolymer of Ethylene and Vinyl Acetate made by high-pressure radical polymerisation process. EVATANE[®] 33-45 PV is stabilized with antioxidants.

Main application

EVATANE[®] 33-45 PV is a dedicated product for photovoltaic applications. EVATANE[®] 33-45 PV brings transparency, flexibility and is compatible with antioxidants and anti UV additives. EVATANE[®] 33-45 PV delivers high dimensional stability through cross-linking formulations.

Specified properties

Characteristics	Value	Unit	Test Method
Vinyl Acetate Content	32 - 34	% wt	FTIR (Internal)
Melt Index (190°C / 2.16 kg)	38 - 48	g/10mn	ASTM D 1238

Physical properties

Characteristics	Value	Unit	Test Method
Density (23°C)	0.96	g/cm ³	ISO 1183
Melting point	62	°C	DSC
Vicat softening point (1 kg)	<40	°C	ASTM D 1525 / ISO 306
Ring & Ball temperature	107	°C	ASTM E28
Elongation at break	900-1100	%	ASTM D 638 / ISO R 527
Tensile strength at break	9	MPa	ASTM D 638 / ISO R 527
Hardness Shore A	63	-	ASTM D 2240 / ISO 868

Processing

EVATANE[®] 33-45 PV can be processed on any kind of conventional equipment used for thermoplastics. EVATANE[®] 33-45 PV should not be overheated during processing and it is recommended to do not have melt temperatures above 230°C and to purge the equipment after a run is completed.

Storage

EVATANE[®] 33-45 PV is available in pellet form and commonly packed in 25 kg PE bags on pallets of 1.375 tons. Other packaging can be considered (ask your Arkema's representative).

Precautions of use

A safety data sheet as well as information on handling and storage of the EVATANE[®] 33-45 PV are available close to your correspondent ARKEMA or on the site www.arkema.com under heading FDS/MSDS.

May 2008

The information contained in this document is based on trials carried out by our Research Centers and data selected from the literature, but shall in no event be held to constitute or imply any warranty, undertaking, express or implied commitment from our part. Our formal specifications define the limit of our commitment. No liability whatsoever can be accepted by Arkema with regard to the handling, processing or use of the products concerned which must in all cases be employed in accordance with all relevant laws and/or regulations in force in the country or countries concerned.



The world is our inspiration
Technical Polymers Division
 420, rue d'Estienne d'Orves
 92705 COLOMBES Cedex
www.arkema.com



www.evataner.com