

TERPOLYMER Ethylene – Vinyl Acetate – Maleic Anhydride

Description

OREVAC-T[®] 9307 Y is a random terpolymer of Ethylene, Vinyl Acetate and Maleic anhydride made by high-pressure radical polymerisation process. **OREVAC-T[®] 9307 Y** is stabilized with antioxidants.

Main applications

OREVAC-T[®] 9307 Y is a material of choice to produce thermo-adhesive films for solid substrates like PA, PET & PU films, Aluminium foils, fiber mats, foams etc. **OREVAC-T[®] 9307 Y** is also used as a skin packaging adhesive on all type of cardboard.

Typical characteristics

Characteristics	Value	Unit	Test Method
Vinyl Acetate Content	13 - 15	% wt	FTIR (internal)
Melt Index (190°C / 2.16 kg)	9.5 – 11.5	g/10mn	ISO 1133 / ASTM D 1238
Maleic Anhydride Content (Mini.)	1600	ppm	FTIR (internal)
Density (23°C)	0.939	g/cm ³	ISO 1183
Melting point	93	°C	DSC
Vicat softening point (10 N)	66	°C	ASTM D 1525 / ISO 306
Ring & Ball temperature	145	°C	ASTM E28
Hardness Shore A / D (15 sec)	91 / 32		ASTM D 2240 / ISO 868

Main properties

- As an ethylene copolymer, **OREVAC-T[®] 9307 Y** is compatible with PE in all proportions, and with almost all other ethylene copolymers.
- Vinyl Acetate brings softness, flexibility and polarity.
- Maleic Anhydride gives reactivity, leading to versatile adhesive properties to polar and non polar substrates in lamination (thermo-adhesive films).
- As a result of high pressure polymerization in tubular reactor, **OREVAC-T[®] 9307 Y** has a high transparency (low haze).

Processing

OREVAC-T[®] 9307 Y can be processed on any kind of conventional equipment used for thermoplastics. It should not be overheated during processing. It is necessary to avoid having molten polymer temperature higher than 230 °C and it is recommended to purge and clean the equipment with product adapted (PEBD etc.) before stopping the machines.

Physical properties

Characteristics	Typical Values on molded sample (1)	Typical Values on blown film (2)	Unit	Test Method
Tensile strength at yield	4.8	5.6 / 5	MPa	ASTM D638(1) / D882(2)
Tensile strength at break	19	26 / 32	MPa	ASTM D638(1) / D882(2)
Elongation at break	600-900	800 / 900	%	ASTM D638(1) / D882(2)
Haze		3.5	%	ASTM D 103
Dart test		180	gr	ASTM D 1709
Young modulus	69	53 / 62	MPa	ISO R 527

(1) On compression molded samples (specimens ISO 527-2, 5A type - thickness 2.8 mm - cross head speed 50mm/min)

(2) On extruded blown films (50 µm thickness, blow up ratio = 2, longitudinal / transverse direction, cross head speed 500mm/min)

Packaging

OREVAC-T[®] 9307 Y is available in pellet form and commonly packed in 25 kg PE bags on pallets of 1.375 tones. Other packaging can be considered (ask your Arkema's representative).

Security / Precautions of use

A safety data sheet as well as information on handling and storage of the **OREVAC-T[®] 9307 Y** are available close to your correspondent ARKEMA or on the web site www.arkema.com under heading FDS/MSDS.

November 2007

The information contained in this document is based on trials carried out by our Research Centers and data selected from the literature, but shall in no event be held to constitute or imply any warranty, undertaking, express or implied commitment from our part. Our formal specifications define the limit of our commitment. No liability whatsoever can be accepted by Arkema with regard to the handling, processing or use of the products concerned which must in all cases be employed in accordance with all relevant laws and/or regulations in force in the country or countries concerned.



Technical Polymers Division
420, rue d'Estienne d'Orves
92705 COLOMBES Cedex
www.arkema.com



www.orevac.com